

RELIABLE STEEL DISTRIBUTORS

(A GOVT. OF INDIA RECOGNIZED EXPORT HOUSE) (A PED CERTIFIED COMPANY)
(ISO 9001 , 14001 & OHSAS 18001 CERTIFIED COMPANY) EMAIL US – sales@rsdplates.com

A 572/A 572M

High-Strength Low-Alloy Columbium-Vanadium Structural Steel¹

1. Scope

1.1 This specification covers five grades of high-strength low-alloy structural steel shapes, plates, sheet piling, and bars. Grades 42 [290], 50 [345], and 55 [380] are intended for riveted, bolted, or welded structures. Grades 60 [415] and 65 [450] are intended for riveted or bolted construction of bridges, or for riveted, bolted, or welded construction in other applications.

1.2 For applications, such as welded bridge construction, where notch toughness is important, notch toughness requirements are to be negotiated between the purchaser and the producer.

1.3 The use of columbium, vanadium, titanium, nitrogen, or combinations thereof, within the limitations noted in Section 5, is required; the selection of type (1, 2, 3, 4, or 5) is at the option of the producer, unless otherwise specified by the purchaser. (See Supplementary Requirement S90.)

1.4 The maximum thicknesses available in the grades and products covered by this specification are shown in Table 1.

1.5 When the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See Appendix X3 of Specification A 6/A 6M for information on weldability.

1.6 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system is to be used independently of the other, without combining values in any way.

1.7 The text of this specification contains notes or footnotes, or both, that provide explanatory material. Such notes and

footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

1.8 For structural products cut from coiled product, the additional requirements, including additional testing requirements and the reporting of additional tests, of A 6/A 6M apply.

2. Referenced Documents

2.1 ASTM Standards:

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling²

A 36/A 36M Specification for Carbon Structural Steel²

A 514/A 514M Specification for High-Yield Strength, Quenched and Tempered Alloy Steel Plate, Suitable for Welding²

3. General Requirements for Delivery

3.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 6/A 6M, for the ordered material, unless a conflict exists in which case this specification shall prevail.

3.1.1 Coiled product is excluded from qualification to this specification until leveled and cut to length. Structural products produced from coil means structural products that have been cut to individual lengths from a coiled product and are furnished without heat treatment. The processor decoils, levels, cuts to length, and marks the product. The processor is responsible for performing and certifying all tests, examinations, repairs, inspections, or operations not intended to affect the properties of the material. For structural products produced from coils, two test results shall be reported for each qualifying coil (Note 1).

NOTE 1—Additional requirements regarding structural products from coil are described in A 6/A 6M.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, and Ships.

Current edition approved Sept. 10, 2001. Published September 2001. Originally

Direct No. :- +91-022-43431324

Fax No. :- +91-022-23894511

Address-29-B Nakoda Bhavan

Sindhi Lane

Mumbai-400004 India

Email :- sales@rsdplates.com

Website www.rsdplates.com


A 572/A 572M
TABLE 1 Maximum Product Thickness or Size

Grade	Yield Point, min		Maximum Thickness or Size				
	ksi	[MPa]	Plates and Bars		Structural Shapes	Sheet Piling	Zees and Rolled Tees
			in.	[mm]	Groups ^A		
42 [290] ^B	42	[290]	6	[150]	all	all	all
50 [345] ^B	50	[345]	4 ^C	[100] ^C	all	all	all
55 [380]	55	[380]	2 1/4	[60]	all	all	all
60 [415] ^B	60	[415]	^D	^D	1, 2, and 3	all	all
^A See Specification A 6/A 6M.	65 [450]	[450]	1 1/4	[32]	1, 2, and 3	not available	all

^AIn the above tabulation, Grades 42, 50, and 60 [290, 345, and 415], are the yield point levels most closely approximating a geometric progression pattern between 36 ksi [250 MPa], min, yield point steels covered by Specification A 36/A 36M and 100 ksi [690 MPa], min, yield strength steels covered by Specification A 514/A 514M.

^CRound bars up to and including 9 in. [225 mm] in diameter are permitted.

^DRound bars up to and including 3 1/2 in. [90 mm] in diameter are permitted.

**TABLE 2 Chemical Requirements^A
(Heat Analysis)**

Diameter, Thickness, or Distance Between Parallel Faces, in. [mm] Plates and Bars	Structural Shapes Groups ^B	Grade	Carbon, max, %	Manganese, ^C max, %	Phosphorus, max, %	Sulfur, max, %	Silicon	
							Plates to 1 1/2 in. [40 mm] in Thickness, Shapes to 426 lb/ft [634 kg/m], Sheet Piling, Bars, Zees, and Rolled Tees ^D	Plates Over 1 1/2 in. [40 mm] in Thickness and Shapes Over 426 lb/ft [634 kg/m]
							max, %	range, %
6 [150]	all	42 [290]	0.21	1.35 ^E	0.04	0.05	0.40	0.15–0.40
4 [100] ^F	all	50 [345]	0.23	1.35 ^E	0.04	0.05	0.40	0.15–0.40
2 [50]	all	55 [380]	0.25	1.35 ^E	0.04	0.05	0.40	0.15–0.40
1 1/4 [32] ^G	1,2,3	60 [415]	0.26	1.35 ^E	0.04	0.05	0.40	H
> 1/2 – 1 1/4 [13–32]	2,3	65 [450]	0.23	1.65	0.04	0.05	0.40	H
# 1/2 [13] ^I	1 ^I	65 [450]	0.26	1.35	0.04	0.05	0.40	H

^ACopper when specified shall have a minimum content of 0.20 % by heat analysis (0.18 % by product analysis).

^BSee Specification A 6/A 6M.

^CManganese, minimum, by heat analysis of 0.80 % (0.75 % by product analysis) shall be required for all plates over 3/8 in. [10 mm] in thickness; a minimum of 0.50 % (0.45 % by product analysis) shall be required for plates 3/8 in. [10 mm] and less in thickness, and for all other products. The manganese to carbon ratio shall not be less than 2 to 1.

^DBars over 1 1/2 in. [40 mm] in diameter, thickness, or distance between parallel faces shall be made by a killed steel practice.

^EFor each reduction of 0.01 percentage point below the specified carbon maximum, an increase of 0.06 percentage point manganese above the specified maximum is permitted, up to a maximum of 1.50 %.

^FRound bars up to and including 9 in. [225 mm] in diameter are permitted.

^GRound bars up to and including 3 1/2 in. [90 mm] in diameter are permitted.

^HThe size and grade is not described in this specification.

^IAn alternative chemical requirement with a maximum carbon of 0.21 % and a maximum manganese of 1.65 % is permitted, with the balance of the elements as shown in Table 2.

4. Materials and Manufacture

4.1 The steel shall be semi-killed or killed

5. Chemical Composition

5.1 The heat analysis shall conform to the requirements prescribed in Table 2 and Table 3.

5.2 The steel shall conform on product analysis to the requirements prescribed in Table 2 and Table 3, subject to the product analysis tolerances in Specification A 6/A 6M.

6. Mechanical Properties

6.1 Tensile Properties:

6.1.1 The material as represented by the test specimens shall conform to the tensile properties given in Table 4.

7. Keywords

7.1 bars; bolted construction; bridges; buildings; columbium-vanadium; high-strength; low-alloy; plates; riveted construction; shapes; sheet piling; steel; structural steel; welded construction

Direct No. :- +91-022-43431324

Fax No. :- +91-022-23894511

Address-29-B Nakoda Bhavan

Sindhi Lane

Mumbai-400004 India

Email :- sales@rsdplates.com

Website www.rsdplates.com


A 572/A 572M
TABLE 3 Alloy Content

Type ^A	Elements	Heat Analysis, %
1	Columbium ^B	0.005–0.05 ^C
2	Vanadium	0.01–0.15
3	Columbium ^B	0.005–0.05 ^C
	Vanadium	0.01–0.15
	Columbium plus vanadium	0.02–0.15 ^D
4	Vanadium	0.01–0.15 ^E
	Nitrogen	0.015 max ^E
5	Titanium	0.006–0.04
	Nitrogen	0.003–0.015
	Vanadium	0.06 max

^AAlloy content shall be in accordance with Type 1, 2, 3, 4, or 5 and the contents of the applicable elements shall be reported on the test report.

^BColumbium shall be restricted to the following thicknesses and sizes unless killed steel is furnished. Killed steel shall be confirmed by a statement of killed steel on the test report, or by a report on the presence of a sufficient quantity of a strong deoxidizing element, such as silicon at 0.10 % or higher, or aluminum at 0.015 % or higher. See table below.

^C Product analysis limits = 0.004 to 0.06 %.

^DProduct analysis limits = 0.01 to 0.16 %.

^EThe vanadium to nitrogen ratio shall be 4 to 1 or greater.

Grades	Maximum Plate, Bar, Sheet Piling, Zees, and Rolled Tee Thicknesses, in. [mm]		Structural Shape Size Groupings (Specification A 6/A 6M, Table A)
42, 50, and 55 [290, 345, and 380]	¾ [20]		Groups 1 and 2 Groups 1 and 2
60 and 65 [415 and 450]	½ [13]		Group 1 Group 1

TABLE 4 Tensile Requirements^A

Grade	Yield Point, min		Tensile Strength, min		Minimum Elongation, % ^{B,C,D}	
	ksi	[MPa]	ksi	[MPa]	in 8 in. [200 mm]	in 2 in. [50 mm]
42 [290]	42	[290]	60	[415]	20	24
50 [345]	50	[345]	65	[450]	18	21
55 [380]	55	[380]	70	[485]	17	20
60 [415]	60	[415]	75	[520]	16	18
65 [450]	65	[450]	80	[550]	15	17

^A See specimen Orientation under the Tension Tests section of Specification A 6/A 6M.

^BElongation not required to be determined for floor plate.

^CFor wide flange shapes over 426 lb/ft [634 kg/m], elongation in 2 in. [50 mm] of 19 % minimum applies.

^DFor plates wider than 24 in. [600 mm], the elongation requirement is reduced two percentage points for Grades 42, 50, and 55 [290, 345, and 380], and three percentage points for Grades 60 and 65 [415 and 450]. See elongation requirement adjustments in the Tension Tests section of Specification A 6/A 6M.

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the order or contract. Standardized supplementary requirements for use at the option of the purchaser are listed in Specification A 6/A 6M. Those that are considered suitable for use with this specification are listed by title:

S5. Charpy V-Notch Impact Test.

S18. Maximum Tensile Strength

S30. Charpy V-Notch Impact Test for Structural Shapes: Alternate Core Location

Direct No. :- +91-022-43431324

Fax No. :- +91-022-23894511

Address-29-B Nakoda Bhavan

Sindhi Lane

Mumbai-400004 India

Email :- sales@rsdplates.com

Website www.rsdplates.com

 **A 572/A 572M**

In addition, the following supplementary requirements are suitable for use:

S81. Tensile Strength

S81.1 For Grade 50 [345] steel of thicknesses $\frac{3}{4}$ in. [20 mm] and less, the tensile strength shall be a minimum of 70 ksi [485 MPa].

S90. Type

S90.1 The specific type of steel shall be as specified by the purchaser in the order or contract.

Direct No. :- +91-022-43431324
Fax No. :- +91-022-23894511
Address-29-B Nakoda Bhavan
Sindhi Lane
Mumbai-400004 India

Email :- sales@rsdplates.com
Website www.rsdplates.com